

Reduction of CO₂ over the TiO₂/ZrO₂ composites covered with a very thin layer of water under solar irradiation

Ichiro Moriya*

Retired Individual Researcher, Japan

With regard to reduction of CO₂, there are many reports [1-4]. Reduction of CO₂ in air is extremely important because this research can not only reduce the concentration of CO₂ in the atmosphere but also can convert the CO₂ into useful compounds including CO, H₂ or low-molecular-weight organic compounds. Here, mini-review is described according to last year's report [5] by author.

Method and experiments

The author devised composites consisting of nanometre-sized titanium oxide (TiO₂) particles (a) and micrometre-sized zirconium oxide (ZrO₂) particles (b), and, applied them using an original method. First, particles or molecules adsorbed onto the composite surface were removed by the elimination of static electricity using an ion blower. Next, after the composites were cooled in a refrigerator for more than 20 h, they were placed into a transparent gas-barrier plastic bag with room air. Cooling in a refrigerator enabled the whole surface of the composite to be covered with a very thin layer of water via the condensation of water vapour in the air. Cleaning of the composite's surface and formation of the thin water layer are extremely important.

Moreover, this method is unique because the reduction of CO₂ is performed in air.

Figure 1 shows SEM image of the composite. The image shows that numerous nanometre-sized TiO₂ particles are present on the top layer of the composite, and the core of the composite is composed of micrometre-sized ZrO₂ particle.

CO₂ was reduced under real solar light without the use of platinum as a co-catalyst.

The weight ratio (TiO₂/ZrO₂) of the composites was mainly 1:1. After (a) and (b) were mixed and pressed to form the composites, the composites were scattered onto an electric conducting material such as a copper plate. Figure 2 shows a typical photograph of the experiment under irradiation by real solar light. Experiments were performed under high room temperatures (approximately 30°C) and high humidity (60-80%). After irradiation, the concentration of formaldehyde and methanol in the bag was measured using gas-detecting tubes.

Results

The author obtained experimental results that reaction was catalytic, and, reaction site existed at interface of TiO₂ and ZrO₂. Then, figure 3 shows plots of formaldehyde and methanol products (μmol/(g·300 s)) as a function of the irradiation intensity of solar light (mW/cm²). This shows that CO₂ reducing reaction was enhanced strongly by the photocatalytic effort.

Conclusion

The thin water layer on the composites provides a reaction medium for the catalytic reduction of CO₂. And, author's method is catalytic




Figure 1. SEM image of the composite




Figure 2. Experiment under irradiation by real solar light

a: Gas-barrier plastic bag with 1000 ml of air; b: Glass laboratory dish containing the composites and Cu plate; c: Composites (TiO₂/ZrO₂=1:1); d: Solar-energy-detecting instrument; e: Solar-energy-detecting sensor.

Correspondence to: Ichiro Moriya, South wing 101, Maebara-nishi 3-6-3, Funabashi, Chiba, Japan, Tel: 047-471-8820, E-mail: moriya260109@yahoo.co.jp

Received: February 28, 2018; **Accepted:** March 19, 2018; **Published:** March 22, 2018




Figure 3. Plots of formaldehyde and methanol products

reaction enhanced by the TiO₂ photo-catalyst. Moreover, the fact that a large amount of reduced products was obtained from CO₂ and H₂O in air under irradiation of only real solar light at room temperature and atmosphere pressure is a novel and important finding.

References

1. Inoue T, Fujishima A, Konishi S, Honda K (1979) Photoelectrocatalytic reduction of carbon dioxide in aqueous suspensions of semiconductor powders. *Nature* 277: 637-638.
2. Low J, Cheng B, Yu J (2017) Surface modification and enhanced photocatalytic CO₂ reduction performance of TiO₂: a review. *Appl Surf Sci* 392: 658-685.
3. Nikokavoura A, Trapalis C (2017) Alternative photocatalysts to TiO₂ for the photocatalytic reduction of CO₂. *Appl Surf Sci* 391: 149-174.
4. Yuan L, Xu YJ (2015) Photocatalytic conversion of CO₂ into value-added and renewable fuels. *Appl Surf Sci* 342: 154-167.
5. Moriya I (2017) Converting of CO₂ into low-molecular-weight organic compounds with the TiO₂/ZrO₂ composites under solar irradiation. *Sci Rep* 7: 14446. [[Crossref](#)]